

PRODUCT INFORMATION



SOLID[®] Chipboard 3 Layers

Deck	chipboard
Core	spruce or poplar staves
Glue	IF 20; AW 100 available on request
Emission class	E1; E0 on request
Format	5200/2600 x 2070 mm
Thickness	16/18/19/22/25/38 mm other thicknesses are available on request
Max. press format	5600 x 2200 mm
Moisture content	8 – 12%
Thickness tolerance	+ 0,2 mm – 0,6 mm
Tolerance in length and width	± 2 mm/m
Squareness tolerance	1 mm/m

Thickness (mm)	E-Modul (N/mm ²) (length)	E-Modul (N/mm ²) (width)	Bending strength (N/mm ²) (length)	Bending strength (N/mm ²) (width)
19	1400	4500	8	35

Multiple applications

Holzindustrie Schweighofer BACO offers the most suitable blockboard for each application.

A wide range of surface and cores ensure various alternatives. Additionally we develop solutions together with our customers, according to their individual requirements.

Significant advantages

- High stability and moisture resistance
- High bending strength
- Light weight
- High screw extraction resistance
- Easy processing

High quality

High quality raw material and longtime experience of our team are the basis for the outstanding quality of our blockboards.

Continuous quality controls ensure stable standards.

All wood that is processed by Holzindustrie Schweighofer BACO comes from PEFC™ controlled sources.

Holzindustrie Schweighofer BACO S.R.L.
Strada Crinului nr. 15, 605200 Comănești, România
T: +40 234 374 052
F: +40 234 374 622

baco.sales@schweighofer.ro
www.schweighofer.ro
www.schweighofer.at

This leaflet is provided for information purposes only and no liability or responsibility of any kind is accepted by Holzindustrie Schweighofer BACO or their representatives, although Holzindustrie Schweighofer BACO has used reasonable efforts to verify the accuracy of any advice, recommendation or information. Holzindustrie Schweighofer BACO reserves the right to alteration of its products, product information and product range without notice.