

PRODUCT INFORMATION



SOLID[©] Light 3 Layers

Deck rotary cut veneer, HDF or chipboard

Core fuma or albasia staves Veneer types

fromager, poplar or beech IF 20

Emission class E1; E0 on request 2070 x 2600/5200 mm **Format Thickness** 13/16/19/22/25/38/50 mm

other thicknesses are available on request

Max. press format 2200 x 5600 mm

Moisture content 8 - 12%

Thickness tolerance + 0,2 mm - 0,6 mm

Tolerance in length and width ± 2 mm/m

Squareness tolerance 1 mm/m

Thickness	kg/m ³	E-Modul	E-Modul	Bending strength	Bending strength
(mm)		(N/mm2) (length)	(N/mm2) (width)	(N/mm2) (length)	(N/mm2) (width)
13	360	3600	3600	24	30
16	360	3600	3600	28	30
19	340	4200	4200	29	28
22	340	4500	4500	35	26
25	330	4800	4800	38	25

Multiple applications

Holzindustrie Schweighofer BACO offers the most suitable blockboard for each application.

A wide range of surface and cores ensure various alternatives. Additionally we develop solutions together with our customers, according to their individual requirements.

Significant advantages

- High stability and moisture resistance
- High bending strength
- Light weight
- High screw extraction resistance
- Easy processing

High quality

High quality raw material and longtime experience of our team are the basis for the outstanding quality of our blockboards.

Continuous quality controls ensure stable standards.

All wood that is processed by Holzindustrie Schweighofer BACO comes from PEFC™ controlled sources.

Holzindustrie Schweighofer BACO S.R.L. Strada Crinului nr. 15, 605200 Comănești, România

T: +40 234 374 052 F: +40 234 374 622

baco.sales@schweighofer.ro www.schweighofer.ro www.schweighofer.at