

PRODUCT INFORMATION



SOLID[®] Prime 3 Layers

Deck	rotary cut veneer, HDF or chipboard
Core	spruce, fuma or poplar staves available in light core
Surface	white paper impregnated with aminoplast resins
Glue	IF 20
Emission class	E1; E0 on request
Format	2070 x 2600/5200 mm
Thickness	13/16/19/22/25/38 mm other thicknesses are available on request
Max. press format	2070 x 5400 mm
Moisture content	8 – 12%
Thickness tolerance	+ 0,2 mm – 0,6 mm
Tolerance in length and width	± 2 mm/m
Squareness tolerance	1 mm/m
Utilization	BACO Prime [®] surface provides the ideal primer paint application. Sanding of the surface not needed.

Multiple applications

Holzindustrie Schweighofer BACO offers the most suitable blockboard for each application.

A wide range of surface and cores ensure various alternatives. Additionally we develop solutions together with our customers, according to their individual requirements.

Significant advantages

- High stability and moisture resistance
- High bending strength
- Light weight
- High screw extraction resistance
- Easy processing

High quality

High quality raw material and longtime experience of our team are the basis for the outstanding quality of our blockboards.

Continuous quality controls ensure stable standards.

All wood that is processed by Holzindustrie Schweighofer BACO comes from PEFC[™] controlled sources.