

# PRODUCT INFORMATION



## SOLID<sup>®</sup> Double Core 5 Layers

Deck	Fromager, poplar or beech rotary cut veneer
Core	Spruce, fuma or poplar staves
Glue	IF 20; AW 100 available on request
Emission class	E1; E0 on request
Format	1870 × 2200 / 2250 mm 1250 × 2200 / 2500 mm
Thickness	34 / 39 / 41 / 44 / 47 / 50 mm Other thicknesses available on request
Max. press format	2200 × 5600 mm
Moisture content	8 – 12%
Thickness tolerance	+ 0,2 mm – 0,6 mm
Tolerance in length and width	± 2 mm/m
Squareness tolerance	1 mm/m

Thickness (mm)	E-Modul (N/mm <sup>2</sup> ) (length)	E-Modul (N/mm <sup>2</sup> ) (width)	Bending strength (N/mm <sup>2</sup> ) (length)	Bending strength (N/mm <sup>2</sup> ) (width)
39.4	2441	6200	17	35

### Multiple applications

Holzindustrie Schweighofer BACO offers the most suitable blockboard for each application.

A wide range of surface and cores ensure various alternatives. Additionally we develop solutions together with our customers, according to their individual requirements.

### Significant advantages

- High stability and moisture resistance
- High bending strength
- Light weight
- High screw extraction resistance
- Easy processing

### High quality

High quality raw material and longtime experience of our team are the basis for the outstanding quality of our blockboards.

Continuous quality controls ensure stable standards.

All wood that is processed by Holzindustrie Schweighofer BACO comes from PEFC™ controlled sources.

Holzindustrie Schweighofer BACO S.R.L.  
Strada Crinului nr. 15, 605200 Comănești, România  
T: +40 234 374 052  
F: +40 234 374 622

baco.sales@schweighofer.ro  
www.schweighofer.ro  
www.schweighofer.at